

FORMULATORS, MANUFACTURERS AND CONSULTANTS OF
SPECIAL CONCRETE PRODUCTS

Newton's Farm Estate, Wissington, Nayland, Suffolk, CO6 4LX, England.

Telephone: 01206 265116 Fax: 01206 265117

Website and e-mail at: www.rockbond.co.uk

ROCKBOND HYDRAULIC LIME MORTAR

DESCRIPTION:

ROCKBOND HYDRAULIC LIME MORTAR (RB HLM) powder is a specially formulated, premixed, ready to use, hydraulic lime mortar powder. The compound contains a fine grade of natural hydraulic lime, quality graded silica sands and a union of compatible admixtures. The powder, when mixed with water, produces a thixotropic, white, low strength, pumping mortar which is specially designed for pressure pointing, and for the filling of joints and voids in brick and stone. The compound is packaged in 25kg moisture proof, durable sacks and has a shelf life of 2 years.

SPECIAL PROPERTIES:

- * Available in white, and also in a range of attractive colours.
- * Quickly and easily mixed, worked, pumped, placed and finished.
- * High build material: thixotropic, cohesive, non-slumping and low shrink.
- * Stable under pressure: can be pumped or injected into place.
- * Microporous: allows brick and stone structures to breathe.
- * Flexible: will move in sympathy with changes in temperature, humidity, stress and differential loading.
- * Low strength and forgiving: a compatible pointing and joint fill material for bricks and blocks.
- * Self healing: microcracks and voids are filled and repaired by continuous carbonation.
- * Economical, non flammable, non toxic, user friendly and safe to use.

USES:

- + For the pressure and hand pointing of concrete, stone, masonry, bricks and blocks.
- + To place, set and lay bricks and blocks, and for bedding in applications.
- + For the pumping, caulking, injecting and filling of cracks, cavities, voids, gaps and joints.
- + As a mortar to repair lime based materials, renders, stone and bricks.
- + To render external brick and stone surfaces to produce an aesthetically pleasing finish.
- + To plaster internal brick and stone substrates to produce a smooth and attractive surface.
- + To restore and make good historic buildings, listed buildings, churches, bridges, viaducts and stone structures.

MIXING INSTRUCTIONS:

ROCKBOND HYDRAULIC LIME MORTAR powder is mixed with water using a ROCKBOND 25 LITRE MIXING CONTAINER (RB 25LMC), a pneumatic or electric power tool (1kW) and a ROCKBOND CONCRETE STIRRER (RB CS). Use a ROCKBOND FORCED ACTION PAN MIXER (RB FAPM) to mix larger amounts of material.

Add 5.00 litres of water to the container or mixer.
Pour 25kg of powder onto the water while mixing.
For batches of 2 or more bags, repeat the procedure.
After all the powder has been added, mix for 30 seconds.
The mortar is now ready for use.

ROCKBOND HYDRAULIC LIME MORTAR (HLM),

MIXING INSTRUCTIONS CONTINUED...

Alternatively, small amounts of the material can be prepared by slowly adding the powder to a quantity of water and mixing to the required consistency.

APPLICATION PROCEDURE:

On weak, friable or porous substrates, use the ROCKBOND PRIMER LATEX (RB PL) to penetrate, consolidate, strengthen and seal the surface. With a brush or a soft broom, brush the latex completely and evenly over the surface. Work the latex well into the substrate. Pay particular attention to the edges of the repair, and brush the liquid at least 25mm beyond the perimeter of the repair area. Let the latex dry out, usually 15 to 20 minutes depending on conditions.

If the substrate requires a primer, or to enhance the bond, apply a second coat of latex to the first coat. Normally, 1 litre of ROCKBOND PRIMER LATEX will treat 5m² of concrete surface with 2 coats of latex.

To point bricks and blocks: rake out all crumbly or weak mortar. Ensure that all surfaces which the mortar comes into contact with are clean and dust free. Use a water spray to washout any debris and to wet the bricks and existing mortar to minimise suction.

For pressure pointing applications: use a ROCKBOND GROUT INJECTION GUN 1 litre (RB GIG1000). Mix the powder with water, charge the gun, and inject the material at the back of the cavity or fissure. Withdraw the nozzle while still injecting to minimise the formation of voids. Bring the level of the mortar up to the profile of the surrounding brickwork, and finish with a steel trowel.

To render brick or cementitious surfaces: remove all friable or weak material; apply one coat of the ROCKBOND PRIMER LATEX to the substrate and let dry. Apply a second coat of the latex and let dry. Or soak the substrate to reduce suction. Mix the mortar powder with water; place by trowel, steel float or spray.

For winter work: protect the mortar from wet weather and frost by covering the material with wet hessian and polyethylene sheet.

TECHNICAL DATA:

ROCKBOND HYDRAULIC LIME MORTAR (HLM)

TYPICAL DATA at 20% water/powder ratio at 20°C

CONSISTENCY:	Wet mortar consistency
CONSISTENCY LIFE:	30 minutes
DENSITY:	1900kg/m ³
COMPRESSIVE STRENGTH:	5MPa at 91 Days
YIELD:	25kg of powder yields 15.00 litres of Hydraulic Lime Mortar 1m ³ of Hydraulic Lime Mortar requires 1.700 tonnes of powder.

ROCKBOND HYDRAULIC LIME MORTAR (HLM), CONTINUED...

HEALTH, SAFETY AND STORAGE:

ROCKBOND HYDRAULIC LIME MORTAR powder is non toxic and safe to use. However, use the same precautions as with any cementitious product: wear goggles, protective clothing and a dust mask while mixing and applying the materials. Consult the relevant MSDS for further details. Store in a cool, dry, dark place.

FURTHER INFORMATION:

Should you require further information on this product, or details of other ROCKBOND SPECIAL CONCRETE PRODUCTS, then please do contact our Technical Department:

Gilbert Cox BSc,
Technical Director,

Rockbond SCP LTD.,
Newton's Farm Estate,
Wissington,
Nayland,
Suffolk,
CO6 4LX.
England.

Telephone: 01206 265116
Facsimile: 01206 265117

Website and e-mail at:
www.rockbond.co.uk

IMPORTANT NOTE:

ROCKBOND SCP LTD provides the above information in good faith and without warranty. The data represents typical values which can be updated at any time, and this information supersedes previous issues. No liability can be accepted for any damage or loss arising from the use of ROCKBOND SCP LTD literature or its products, because the company has no continuous control on how the products are mixed, placed or cured.

APRIL 2011